

PCT

ORGANISATION MONDIALE DE LA PROPRIÉTÉ INTELLECTUELLE
Bureau international

INDEXÉ



DEMANDE INTERNATIONALE PUBLIÉE EN VERTU DU TRAITE DE COOPERATION EN MATIERE DE BREVETS (PCT)

(51) Classification internationale des brevets 7 : B65D 35/12, B29C 45/16, B29D 23/20	A1	(11) Numéro de publication internationale: WO 00/23340
		(43) Date de publication internationale: 27 avril 2000 (27.04.00)

(21) Numéro de la demande internationale: PCT/FR99/02525

(22) Date de dépôt international: 18 octobre 1999 (18.10.99)

(30) Données relatives à la priorité:
98/13223 19 octobre 1998 (19.10.98) FR(71) Déposant (pour tous les Etats désignés sauf US): CEBAL SA
[FR/FR]; 98, boulevard Victor Hugo, F-92115 Clichy (FR).

(72) Inventeurs; et


(75) Inventeurs/Déposants (US seulement): MEAUSOONE,
Jean-Paul [FR/FR]; 94, rue du Barbatre, F-51100
Reims (FR). BOSSHARDT, Michel [FR/FR]; 39, rue
Camille Margaine, F-51800 Sainte-Menehould (FR). LA-
PALUS, Roger [FR/FR]; 50, rue Gaillot Aubert, F-51800
Sainte-Menehould (FR).(74) Mandataire: PIGASSE, Daniel; Pechiney, 28, rue de Bonnel,
F-69433 Lyon Cedex 03 (FR).(81) Etats désignés: BR, CA, CN, CZ, ID, IN, JP, KR, MX, PL,
RU, US, brevets européens (AT, BE, CH, CY, DE, DK, ES,
FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Publiée

Avec rapport de recherche internationale.

(54) Title: TUBE WITH MULTILAYER HEAD AND METHOD FOR MAKING SAME

(54) Titre: TUBE A TETE EN MATERIAUX MULTICOUCHEES ET PROCEDE DE FABRICATION



(57) Abstract

The invention concerns a plastic tube head (2), designed to be assembled with a skirt (3) to form a tube (1), comprising a neck (20), and a shoulder (21), characterised in that: a) said head (2) includes a multilayer material comprising an inner layer (24), and an outer layer (23) made of structural material A, characteristically a polyolefin, and an inner layer (25) made of a thermoplastic barrier material; b) said inner layer (25) is coated by said inner (24) and outer (23) layers, up to and including the ends (250, 251) of said head where said inner and outer layers are assembled into one material A layer, the distance "e" and "e'" between each of the ends of said inner layer and the corresponding end of said head ranging between 0.02 and 5 mm.